

# Gold Medalist® Wood Seal

HILLYARD  
FIRST IN GYM FINISHES®

A state-of-the-art, solvent-based urethane seal that sets the standards by which all other urethane seals are judged. Gold Medalist Seal penetrates evenly into the surface of the wood to give added strength and protection as well as provide the perfect foundation for Gold Medalist® Wood Gym Finish. Together, Gold Medalist Seal and Finish bond to give wood gym floors the tough protection needed for tournament play.

## Features & Benefits

- Top quality urethane seal and finish.
- Fast and easy to apply.
- Penetrates evenly into wood surface.

## Directions

**PREPARATION: NEW OR FRESHLY SANDED WOOD:** Proper floor preparation and adherence to label directions are critical for successful results. After the floor has been properly sanded and screened, brush sweep and vacuum until surface and cracks are free of sanding dust. Tack the floor with terry cloth towels dampened with HILLYARD KLEEN-UP SOLVENT. Allow the floor to dry a minimum of one hour.

**APPLICATION:** Before applying GOLD MEDALIST WOOD SEAL, tack the floor a final time with a cleaning cloth similar to HILLYARD Item CHI415. Apply seal at a coverage rate of 350-500 square feet per gallon with a lambswool applicator, E-Z WAY, HILLYARD MULTI-FLO, or HILLYARD weighted T-Bar applicator. Two coats of GOLD MEDALIST SEAL is recommended for new or freshly sanded floors. Avoid leaving puddles of seal on the floor. Allow first coat to dry at least 12 hours, abrade with maroon pads (250 sq. ft. per side of pad), or 120 grit screen discs (250 sq. ft. per side of screen) and tack with HILLYARD TACK-IT. Allow floor to dry one hour. If seal dries longer than 48 hours, abrade with discs (150-100 grit, depending on how long it has dried). Apply the second coat of seal. After second coat of seal is dry and abraded as above, tack with TACK-IT before applying any game lines. Use only HILLYARD approved paints. Allow to dry overnight, abrade with maroon pads, and tack with TACK-IT. Apply two coats of HILLYARD FINISH.

**NOTE:** Turn on the exhaust system four hours after each application of GOLD MEDALIST SEAL. If after abrading, the floor sits for longer than 24 hours before being coated, re-abrade and tack before applying additional seal coats to prevent peeling from occurring. On newer floors be cautious not to flood expansion joints with excess seal and finish.

**MAINTENANCE:** Dust mop daily with Hillyard Super Hil-Tone, Hil-Mist, or Hil-Treat. Clean badly soiled floors with Super Shine-All. Refer to the Hillyard First in Wood Gym Floor Care Manual for complete details on care.

**NOTICE:** Best results are obtained with adequate ventilation and floor temperatures above 60 deg.F (16 deg.C) and below 95 deg.F (35 deg.C). Avoid direct drafts on floor while sealing. Do not store partially full containers of material for long periods of time. Do not pour unused material back into container. Empty containers may retain hazardous residue and explosive vapors. Keep away from heat, sparks, and flames. Do not cut, puncture, or weld on or near this container. Follow label warnings until container is thoroughly cleaned or destroyed.

**NOTICE:** Saw dust from freshly sanded floors or dust from wood floors that have been abraded between coats will spontaneously catch fire if improperly discarded. Immediately after abrading or sanding wood floors, place dust waste in a sealed, water-filled metal container and immediately remove from building.

**NOTICE:** Rags or applicators soaked in a combustible liquid will spontaneously catch fire if improperly discarded. Immediately after using rags or applicators soaked in a combustible liquid, place waste in a sealed, water-filled metal container and immediately remove from building.

## Certifications, Registrations & Notes

Classified by Underwriters Laboratories, Inc.® as to slip resistance. (1865)  
Approved by the Maple Flooring Manufacturers Association, Inc.



## Safety

See material safety data sheet and product label for safety information, handling and proper use.

## HMIS

	Concentrate
Health	2
Flammability	2
Reactivity	0

## Technical Specifications

Color	Clear Amber
Scent	Solvent
Appearance	Clear
pH (concentrate)	N/A
Non-Volatile Matter	35.00%
Dilution Rate	RTU

## Availability

Item	Pack
HIL0032607	1 - 5 Gallon Pail

HILLYARD

P.O. Box 909  
St. Joseph, MO 64502  
1-800-365-1555  
www.hillyard.com