

Trophy® Wood Seal

HILLYARD
FIRST IN GYM FINISHES®

When maintenance professionals think of wood gym floor seals and coatings, they think of Hillyard first. And Hillyard's Trophy Wood Seal is the state-of-the-art epoxy seal that has been setting the standard for excellence for decades. It is formulated to penetrate the surface of the floor evenly, becoming an integral part of the wood, giving it strength and optimum protection. At the same time, Trophy Wood Seal provides the perfect foundation for Trophy Gym Finish. Together, Trophy Wood Seal and Gym Finish stand up under the busiest schedules, resisting rubber burns, heel marks, dust, and dirt.

Features & Benefits

- Durable epoxy base penetrates the floor evenly.
- The perfect foundation for Trophy Gym Finish.
- Resists rubber burns, heel marks, dust, and dirt.

Directions

SURFACE PREPARATION: NEW OR FRESHLY SANDED WOOD: After the floor has been properly sanded and screened, brush, sweep and vacuum until surface and cracks are free of sanding dust. Tack the floor with terry cloth towels dampened with HILLYARD KLEEN-UP SOLVENT Allow the floor to dry a minimum of one hour.

APPLICATION: Before applying TROPHY WOOD SEAL, tack the floor a final time with a cleaning cloth similar to HILLYARD Item CHI415. Apply seal at a coverage rate of 350- 500 square feet per gallon with a lambswool applicator, heavy weight T- Bar or HILLYARD MULTI-FLO applicator. Avoid leaving puddles of seal on floor. Allow the coating to dry at least 12 hours, abrade with maroon pads (250 sq. ft. per side of pad), and tack with HILLYARD TACK-IT or Hillyard PRE-GAME solution. Allow floor to dry one hour. If seal cures longer than 48 hours, abrade with discs 150-100 grit depending on how long the seal has cured). Sealing is a most important step. When properly sealed, the floor will show no dull spots. Apply an additional coat if necessary. After second coat of seal is dry and abraded as above, tack with TACK-IT or PRE-GAME solution before applying any game lines. Use only HILLYARD approved paint.

NOTE: Turn on the exhaust system two to four hours after each application of TROPHY SEAL.

NOTICE: Best results are obtained with adequate ventilation and floor temperatures above 60 deg.F (16 deg.C) and below 95 deg.F (35 deg.C). Avoid direct drafts on floor while finishing. Do not store partially full containers of material for long periods of time. Do not pour unused material back into container. Empty containers may retain hazardous residue and explosive vapors. Keep away from heat, sparks, and flames. Do not cut, puncture, or weld on or near this container. Follow label warnings until container is thoroughly cleaned or destroyed.

NOTICE: Saw dust from freshly sanded floors or dust from wood floors that have been abraded between coats will spontaneously catch fire if improperly discarded. Immediately after abrading or sanding wood floors, place dust waste in a sealed, water-filled metal container and immediately remove from building.

NOTICE: Rags or applicators soaked in a combustible liquid will spontaneously catch fire if improperly discarded. Immediately after using rags or applicators soaked in a combustible liquid, place waste in a sealed, water-filled metal container and immediately remove from building.

Certifications, Registrations & Notes

Classified by Underwriters Laboratories, Inc.® as to slip resistance. (1865)
Approved by the Maple Flooring Manufacturers Association, Inc.



Safety

See material safety data sheet and product label for safety information, handling and proper use.

HMIS

Concentrate

Health	2
Flammability	2
Reactivity	0

Technical Specifications

Color	Clear Amber
Scent	Solvent
Appearance	Clear
pH (concentrate)	N/A
Non-Volatile Matter	28.00%
Dilution Rate	RTU

Availability

Item	Pack
HIL0035207	1 - 5 Gallon Pail

HILLYARD

P.O. Box 909
St. Joseph, MO 64502
1-800-365-1555
www.hillyard.com