# Satin Floor Finish

A special low gloss floor coating. It lowers the cost of clean by lowering the frequency of cleaning. It provides excellent resistance to black marks, scuffs, scratches, and heel marks. No buffing is required or desired. Recommended for assisted living and nursing homes, especially those that are dedicated to the care of Alzheimer's patients. Also recommended for other situations where a low gloss surface or minimal reflection is desired. Geriatric experts have concluded that shiny surfaces may appear wet to an Alzheimer's patient.

## **Features & Benefits**

- Special low gloss floor coating.
- Recommended for assisted living and nursing homes.
- No buffing is required or desired.

### **Directions**

**PREPARATION:** Strip other finishes from the floor with HILLYARD DEVASTATOR or POWER-STRIP following label directions. Use floor machine with black pad or brush (do not use abrasive pads on tile containing asbestos). Remove stripping solution with a wet vacuum. Heavy rinse with HILLYARD NUTRA-RINSE mixed 4 oz. per gallon of water and pick up with the wet vacuum. Damp mop all flooring twice with clean, cool water. Allow the floor to dry.

**APPLICATION:** Before opening container, gently and slowly rock it back and forth for 10 seconds to mix flatting agent. Do not use a sealer. Apply 3 to 5 coats of SATIN FLOOR FINISH with a clean synthetic flat mop. Allow each coat to dry a minimum of 30 minutes before applying the next. For best results do not use over existing floor finish or sealer as this will affect gloss, and do not coat over SATIN FLOOR FINISH with another finish. Apply with a flat mop applicator only.

**NOTE:** Allow for longer dry time between coats of finish if the humidity is above 80% or the floor temperature is below 60°F (16°C).

**FLOOR PAD RECOMMENDATIONS: Strip** - black; **Scrub and Recoat** - blue or green; **Autoscrubbing** - red.

**NOTICE:** Do not use an ammoniated cleaner for daily care. Do not pour unused finish or seal back into the original container.

## **Certifications, Registrations & Notes**

Classified by Underwriters Laboratories, Inc.® as to slip resistance. (186S).





## **Safety**

See material safety data sheet and product label for safety information, handling and proper use.

| HMIS         | Concentrate |
|--------------|-------------|
| Health       | 1           |
| Flammability | 0           |
| Reactivity   | 0           |

## **Technical Specifications**

| White             |
|-------------------|
| Non-Objectionable |
| Milky Emulsion    |
| 8.00 - 9.00       |
| 20.00%            |
| RTU               |
|                   |

#### **Availability**

| Item       | Pack                    |
|------------|-------------------------|
| HIL0054006 | 4 - 1 Gallon Containers |

**Coverage Rates:** 1,500 - 2,000 Sq. Ft. per Gallon Rates can very greatly based on surface and application method.



P.O. Box 909 St. Joseph, MO 64502 1-800-365-1555 www.hillyard.com