

# Trophy® Gym Finish

HILLYARD  
FIRST IN GYM FINISHES®

The state-of-the-art epoxy finish that has been setting the standard for excellence for decades. Trophy is formulated to stand up under the busiest schedules, resisting rubber burns, heel marks, dust, and dirt. Its durable epoxy base requires minimal daily care and provides long-lasting protection without the need for excessive re-coating.

## Features & Benefits

- Durable epoxy finish does not yellow with age.
- Provides long-lasting protection.
- Requires minimal daily care.

## Directions

**PREPARATION: NEW OR FRESHLY SANDED WOOD:** After the floor has been sealed and game lines painted, abrade with maroon pads (250 sq. ft. per side of pad). Place a white pad between the pad holder and maroon pad. Tack the floor with HILLYARD TACK-IT or HILLYARD PRE-GAME solution. Allow floor to dry one hour.

**SCRUB AND RE-COAT:** Scrub with 2 oz. of HILLYARD SUPER SHINE-ALL per gallon of water or PRE-GAME solution, using 120 grit screen disc (500 sq. ft. per side of disc) under a single brush floor machine (use a white pad between the pad holder and the disc). Pick up the solution with a wet vacuum and damp mop rinse twice with clean water. Work small areas and do not flood the floor. Allow the floor to dry overnight. Tack the floor with terry cloth towels dampened with TACK-IT or PRE-GAME solution. Allow floor to dry one hour. If you choose to dry screen the floor, be sure to sweep, vacuum, and tack until the floor is completely dust free.

**APPLICATION:** Before applying TROPHY, tack the floor a final time with a cleaning cloth similar to HILLYARD Item CHI415. Apply finish at a coverage rate of 500-600 square feet per gallon with a lambswool applicator, HILLYARD MULTI-FLO, or HILLYARD weighted T-Bar applicator. Avoid leaving puddles of finish on floor. Allow the coating to dry at least 12 hours, abrade with maroon pads, and tack with TACK-IT or PRE-GAME solution. If finish cures longer than 48 hours, abrade with discs (150-100 grit depending on how long the finish has cured). Apply the final coat. Do not use floor for at least 72 hours and wait one week for scheduled activities.

**NOTE:** Turn on the exhaust system four hours after each application of Trophy Gym Finish. If after abrading, the floor sits for longer than 24 hours before being coated, re-abrade and tack before applying additional seal or finish coats to prevent peeling from occurring. On newer floors be cautious not to flood expansion joints with excess seal and finish.

**PAINT:** Prior to re-coating, use HILLYARD approved paint following label directions to touch up game lines. Worn areas should be patched in with Trophy prior to re-coating the entire floor.

**MAINTENANCE:** Dust mop daily with Hillyard Super Hil-Tone, Hil-Mist, or Hil-Treat. Clean badly soiled floors with Super Shine-All.

**NOTICE:** Best results are obtained with adequate ventilation and floor temperatures above 60 deg. F (16 deg. C). Avoid direct drafts on floor while finishing. Do not store part- full containers of material for long periods of time. Do not pour unused material back into container. Empty containers may retain hazardous residue and explosive vapors; do not pressurize, cut, weld, braze, solder, drill, or grind container.

**NOTICE:** Saw dust from freshly sanded floors or dust from wood floors that have been abraded between coats will spontaneously catch fire if improperly discarded. Immediately after abrading or sanding wood floors, place dust waste in a sealed, water-filled metal container and immediately remove from building.

**NOTICE:** Rags or applicators soaked in a combustible liquid will spontaneously catch fire if improperly discarded. Immediately after using rags or applicators soaked in a combustible liquid, place waste in a sealed, water-filled metal container and immediately remove from building.

## Certifications, Registrations & Notes

Classified by Underwriters Laboratories, Inc.® as to slip resistance. (1865)



## Safety

See material safety data sheet and product label for safety information, handling and proper use.

### HMIS

|              | Concentrate |
|--------------|-------------|
| Health       | 2           |
| Flammability | 2           |
| Reactivity   | 0           |

## Technical Specifications

|                     |             |
|---------------------|-------------|
| Color               | Clear Amber |
| Scent               | Solvent     |
| Appearance          | Clear       |
| pH (concentrate)    | N/A         |
| Non-Volatile Matter | 40.00%      |
| Dilution Rate       | RTU         |

## Availability

| Item       | Pack                    |
|------------|-------------------------|
| HIL0028306 | 6 - 1 Gallon Containers |
| HIL0028307 | 1 - 5 Gallon Pail       |

HILLYARD®

P.O. Box 909  
St. Joseph, MO 64502  
1-800-365-1555  
www.hillyard.com